



TOPFLOOR

Acrytop acrylic system

COLOR COAT

DESCRIPTION

TOPFLOOR color coat is 100% acrylic binder , water based , high uv resistance outdoor sports flooring paint.
SURFACE PREPARATION

Dust, oil, foreign substances must be removed from the surface. The temperature of the surface must be between 10C to 30C.

MIXING RATIO AND CONSUMPTION

1ST LAYER: TOPFLOOR color coat (500-600gr/sq mt) + 40%-50% silica sand + 20% -30% water.
2nd Layer: TOPFLOOR color coat (250-350gm/sq mt) + 10%-20% silica sand + 30% -40% water.
3rd Layer : TOPFLOOR color coat (150-200gm/Sq mt) + 10% -25% water for fast courts *if the court surface is required to be slower, Silica sand percentage 5%-10% could be added.

APPLICATION AND CLEANING EQUIPMENT

TOPFLOOR color coat is applied with squeegee, Each color coat layer must be applied to the surface in a different direction (for e.g. if the first layer has been applied horizontally, 2nd layer must be done vertically and then the final layer again horizontally) Clean the tools and equipment with water after use.

PACKAGING AND STORAGE

TOPFLOOR color is available in 60 kg plastic drums, should be stored at room temperature, storage area climate condition should not be above 35C and below 5C. If stored in appropriate conditions, the shelf life of TOPFLOOR cushion is 12 months from the date of manufacturer. Material must be protected from freezing.

TECHNICAL DATA

Product : TOPFLOOR color coat

Binder : 100% acrylic

Drying time : 1 hour (25C) 2-6 hours wait for apply the second layer, should be observed that the surface completely dry.

Color : Shade card

Theoretical consumption: TOPFLOOR cushion theoretical consumption is 350-500gm/Sq mt

