

Report Number: BGLA25007068





TEST REPORT

NUMBER : BGLA25007068 DATE : 02-Aug-2025

APPLICANT : Topfloor Sports Infra Private Limited

Survey No.199, Vaghroda, Village -

Vaghroda, Taluka - Kadi, Mehsana, Mehsana,

Gujarat, 382715, India

ATTN : Lalit Sondarva

SELF REFERENCE

Sample Description As Declared: : One Pack of Granules Sample Submitted.

Sample Description : EPDM Granules

Country of Destination : India

Date Received/date Test Started : 31 Jul 2025

Buyer Name. : -

Date Confirmation Received : 31 Jul 2025

P.O.No : Article No. : Fiber Content : Style : -

Color : Royal Blue-Identified by Lab

Manufacturer's Name : Topfloor

TEST CONDUCTED: AS PER THE REQUEST OF THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO ENCLOSED PAGE(S)

AUTHORIZED BY

FOR Intertek India Private Limited [Analytical - Bangalore]

SURESHKUMAR B ASSISTANT MANAGER



TEST REPORT

NUMBER : BGLA25007068 DATE : 02-Aug-2025

CONCLUSION:

Polycyclic Aromatic Hydrocarbons (Pah)

* *

Note: M = Meets Requirement F = Fails To Meet Requirement

* = Requirement Not Provided NA = Not Applicable
= Exempted NC = No Comment
SC = See Comment ** = Refer Result

= Not Performed MA = Marginal Acceptance

NR = Not Requested D = Data Only

C = Confirm Label

- 1. Statement of conformity is based on the simple acceptance rule without using measurement uncertainty.
- 2. In this report results relate only to the item tested.
- 3. Laboratory reports the final test results in test report. Any additional information, if required will be provided on request.
- 4. Samples received in good condition.
- 5. Testing has been performed as per the applicant's request.
- 6. Sampling is not done by Laboratory.
- 7. Environmental conditions followed at the time of testing as per International methods/customer requirements.



TEST REPORT

NUMBER : BGLA25007068 DATE : 02-Aug-2025

Test Conducted (As Requested By The Applicant)

1. Polycyclic Aromatic Hydrocarbons (Pah)

AFPS-GS-2019-01-PAK:2020. Extraction with Toluene Determination With GC-MS Analysis.)

		<u>Requirement</u>
Naphthalene	BDL	Not Provided
Acenaphthylene	BDL	
Acenaphthene	BDL	
Fluorene	BDL	
Phenanthrene	3.55 PPM	
Anthracene	BDL	
Fluoranthene	BDL	
Pyrene	0.65 PPM	
Chrysene	BDL	
Benzo [A] Anthracene	BDL	
Benzo [B] Fluoranthene	BDL	
Benzo [K] Fluoranthene	BDL	
Benzo [J] Fluoranthene	BDL	
Benzo [E] Pyrene	BDL	
Benzo [A] Pyrene	BDL	
Dibenz [A, H] Anthrancene	BDL	
Indeno [1,2,3 Cd] Pyrene	BDL	
Benzo [G, H, I] Perylene	BDL	
Sum of All 18 Pahs	4.20 PPM	

REMARK:

[A]: EPDM GRANULES ROYAL [BLUE]

BDL: BELOW DETECTON LIMIT

PPM(Parts per Million) = mg/kg (Milligram per Kilogram)

DETECTION LIMIT: 0.2 PPM

END OF THE TEST REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Addressee in respect of this report and only accepts liability to the Addressee insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute.

http://www.intertek.com/terms.