

# TEST CERTIFICATE

Sample : Acrytop Topcoat	Report No. : 21010262/B
Sample Description: Acrytop Topcoat	
Party's Ref No.: Nil	Report Issue Date: 05/09/2023
Customer Name & Address : Topfloor Sports Infra Pvt. Ltd. Survey No. 199, at: Vaghroda Nr. Khavad Village Kadi- Kalyanpura Road, Dist: Mahesana-384445, Gujarat.	Job Code : STRC/21010262 Sample Received On : 12/08/2023 Date of Testing : 12/08/2023 To 05/09/2023 Sample quantity : 1 Ltr.
Sample Condition	Filled in Plastic Can

## TEST RESULTS

S.No.	Test Parameter	Results	Test Method
<b>Chemical Testing-Paint &amp; Surface Coating-Others</b>			
1	Drying Time, minutes	--	IS:101(P-3/Sec-1)1986
	Surface dry	45	--
	Hard dry	60	--
	tack free	180	--
2	Cross Hatch Adhesion	4B (<5% area removed)	IS:101(P-5/Sec-2)1988 (Amnd- 3)
3	Resistance to Alkali	Passes the test	IS: 428-2000
4	Coating Hardness (Pressure Hardness)	No metal surface rendered	IS: 101 (P-5/Sec-1) 1988
5	Color Fade Test (UV Light Test-100 Hrs)	No color change found	ASTM G154
6	Scratch Hardness (1000gm)	No scratch found	IS: 101 (P-5/Sec-2) 1988

**Decision Rule:** The decision rule as per SOP DR01 is applied wherever statement of conformity to a specification or standard provided in the test report.

\*\*\*\*\*End of Report\*\*\*\*\*

21010262/B-1



Format No.: STRC/7.8/F/TC/Z/03

*Santram Rajput*

Santram Rajput  
Technical Manager

Page No.: 1 of 1

Scan QR Code to verify the authenticity of Report.

(1) The Test results listed refer only to tested samples and applicable parameters. Endorsement of product is neither inferred nor implied. (2) Total liability of our Lab is limited to the invoiced amount. (3) Sample(s) are retained for 7 days (in case of perishable items) and 30 days for non perishable samples or unless otherwise specified. (4) This Test Report is not to be reproduced wholly or in part and cannot be used as an evidence in the court of Law and should not be used in any advertising media without our special permission in writing. (5) The Test Report refer to the sample submitted to us and not drawn by Sigma Test & Research Centre unless mentioned otherwise.